



**Ragno USA, Inc**  
 359 Clay Road  
 Sunnyvale, TX 75182  
 USA

Telephone: (972) 232 3802  
 Fax: (972) 725 3127  
 Toll Free: 888 297 2466  
 E-mail: info@ragnousa.com

**BURGUNDY**

*Floor Tile*

Burgundy take inspiration from nature, recreates warm and shadowed surfaces, mix the strength and durability of glazed porcelain stoneware, open new possibilities for personal and exclusive designed interiors.



AF3N Burgundy GR  
20"x20"



AF3P Burgundy GO  
20"x20"



AF3O Burgundy NO  
20"x20"



AF3R Burgundy TC  
20"x20"

AF3J Burgundy GR  
13"x13"

AF3K Burgundy GO  
13"x13"

AF3L Burgundy NO  
13"x13"

AF3M Burgundy TC  
13"x13"

AF56 Burgundy GR  
6½"x6½"

AF57 Burgundy GO  
6½"x6½"

AF58 Burgundy NO  
6½"x6½"

AF59 Burgundy TC  
6½"x6½"




AG58 Burgundy GR  
Mosaic Square  
13"x13"



AG59 Burgundy GO  
Mosaic Square  
13"x13"



AG6A Burgundy NO  
Mosaic Square  
13"x13"



AG6B Burgundy TC  
Mosaic Square  
13"x13"



AF62 Burgundy GR  
Listelli  
1"x13"



AF63 Burgundy GO  
Listelli  
1"x13"



AF64 Burgundy NO  
Listelli  
1"x13"



AF65 Burgundy TC  
Listelli  
1"x13"



AF67 Burgundy Corner  
Insert  
1"x1"



AF3S Burgundy GR  
SBN  
3"x13"

AF3T Burgundy GO  
SBN  
13"x3"

AF3U Burgundy NO  
SBN  
13"x3"

AF3V Burgundy TC  
SBN  
13"x3"



AF5E Burgundy GR  
Bead  
6½"x1"

AF5F Burgundy GO  
Bead  
6½"x1"

AF5G Burgundy NO  
Bead  
6½"x1"

AF5H Burgundy TC  
Bead  
6½"x1"



AF5J Burgundy GR  
Beak  
1"x1"

AF5K Burgundy GO  
Beak  
1"x1"

AF5L Burgundy NO  
Beak  
1"x1"

AF5M Burgundy TC  
Beak  
1"x1"



AF5N Burgundy V-Cap  
GR  
6½"x2¼"

AF5P Burgundy GO V-  
Cap  
6½"x2¼"

AF5Q Burgundy NO V-  
Cap  
6½"x2¼"

AF5R Burgundy TC V-  
Cap  
6½"x2¼"




AF5S Burgundy GR V-  
Cap Corner  
2¼"x1¾"

AF5T Burgundy GO V-  
Cap Corner  
2¼"x1¾"

AF5U Burgundy NO V-  
Cap Corner  
2¼"x1¾"

AF5V Burgundy TC V-  
Cap Corner  
2¼"x1¾"

### SHADE VARIATION AND APPLICATIONS

<b>V3</b>		Residential	Commercial	Industrial
 MODERATE VARIATION	Floor	•	•	
	Wall	•	•	•
	Countertop	•	•	•
	Pool	•	•	•

### TECHNICAL SPECIFICATIONS

DESCRIPTION	ANSI STANDARD	RESULT	ASTM TEST METHOD	
Water Absorption	≤ 0.50%	≤ 0.50%	C373	
Frost Resistance	As Reported	Resistant	C1026	
Scratch Resistance	MOHS 1-10	6	MOHS SCALE	
Breaking Strength	20"x20"	≥ 250 lbf.	≥ 530 lbf.	C648
	13"x13"	≥ 250 lbf.	≥ 400 lbf.	C648
Facial Dimension	-3.0 % < Nominal < 3.0 %	Within Standard	C499	
Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499	
Wedging (Squareness)	+/- 0.50 % or +/- 2.0 mm*	Within Standard	C502	
Warpage (Flatness)	+/- 0.75 % or +/- 2.3 mm*	Within Standard	C485	
Abrasion Resistance	Class 0 - Class V	Class IV	C1027	
C.O.F. (Wet)	As Reported	0.60 ≤ COF < 0.70	C1028	
C.O.F. (Dry)	As Reported	0.70 ≤ COF < 0.80	C1028	
Chemical Resistance	Class A - Class E	Class A	C650	
Stain Resistance	Class A - Class E	Class A	C1378	

\* Whichever is less